



Cite this: *New J. Chem.*, 2020, **44**, 11384

## Correction: Second-order nonlinear optical properties of eight-membered centrosymmetric cyclic borasiloxanes

Mohan Gopalakrishnan, <sup>ab</sup> Thamodharan Viswanathan, <sup>a</sup> Ezhumalai David, <sup>a</sup> Krishnan Thirumoorthy, <sup>a</sup> Nattamai S. P. Bhuvanesh<sup>c</sup> and Nallasamy Palanisami <sup>\*a</sup>

DOI: 10.1039/d0nj90069a

rsc.li/njc

Correction for 'Second-order nonlinear optical properties of eight-membered centrosymmetric cyclic borasiloxanes' by Mohan Gopalakrishnan *et al.*, *New J. Chem.*, 2019, **43**, 10948–10958, DOI: 10.1039/C9NJ01611B.

The authors regret that some polarizability ( $\alpha_0$ ) and first hyperpolarizability ( $\beta_0$ ) values in Table 2 were incorrect in the original manuscript. The updated Table 2 is shown below.

**Table 2** The calculated chemical potential ( $\mu$ ), chemical hardness ( $\eta$ ), electrophilicity index ( $\omega$ ), dipole moment ( $\mu_{\text{total}}$ ), polarizability ( $\alpha_0$ ) and first hyperpolarizability ( $\beta_0$ ) of borasiloxanes **1–5**

Compound	$\mu$	$\eta$	$\omega$	$\mu_{\text{total}}$	$\alpha_0 \times 10^{-24}$ esu	$\beta_0 \times 10^{-32}$ esu
<b>1</b>	−0.149	0.106	0.105	0.001	73.046	37.209
<b>2</b>	−0.153	0.102	0.115	0.001	73.290	51.838
<b>3</b>	−0.165	0.101	0.135	0.013	77.437	52.190
<b>4</b>	−0.174	0.095	0.159	0.002	79.150	77.610
<b>5</b>	−0.190	0.080	0.226	0.010	79.560	87.576

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

<sup>a</sup> Department of Chemistry, School of Advanced Sciences, Vellore Institute of Technology, Vellore 632 014, Tamil Nadu, India. E-mail: palanisami.n@gmail.com; Tel: +91 98426 39776

<sup>b</sup> Department of Chemistry, Karpagam Academy of Higher Education, Coimbatore-641021, Tamil Nadu, India

<sup>c</sup> X-ray Diffraction Lab, Department of Chemistry, Texas A&M University, College Station, TX 77842, USA

