

Usage of Carbon nanotubes and nano fibers in cement and concrete: A review

A.Vijayabhaskar ^{#1}, Shanmugasundaram M ^{*2}

[#] Research scholar, School of Mechanical and Building sciences,
VIT University (Chennai Campus), India
¹vijaya.bhaskar2016@vitstudent.ac.in

^{*} Assistant professor, School of Mechanical and Building sciences,
VIT University (Chennai Campus), India
²shanmugaresearch@gmail.com

Abstract- Carbon Nanotubes (CNTs) are basic carbon consisting of curved graphene layer which consists of a single layer of atoms in a combined hexagonal structure. After plenty of years several characterization of the carbon Nanotubes has become very popular in various applications in civil engineering. Carbon Nanotubes shows good results in terms of mechanical properties of cement mortar when added to it. Literature has showed that carbon Nanotubes can be used in the manufacture of the concrete and the cement pastes. This paper represents the summary of the various research works on the usage of the carbon nanotubes in cement paste, mortars and concrete.

Keywords- Carbon Nanotubes (CNTs), graphene layer, hexagonal structure Carbon, cement paste, mortars, concrete

I. INTRODUCTION

Lijma and his group discovered the carbon Nanotubes in the year of 1991 there after growing the special interest in the CNTs [1].CNTs are available in the form of hollow tubular channels, and also formed either by Single-walled Carbon Nanotubes (SWCNTs) and multi-walled Carbon Nanotubes (MWCNTs) of rolled graphene sheet [2, 3].Most of the researchers and industrial persons show their special interest because of their extraordinary physical properties as well as chemical properties. These properties will be useful in different applications from existing matter in to Nano sized meter composites [4, 5].Carbon Nanotubes are circulated in a finer scale when compared to Carbon Nanofibers, Carbon Nanotubes depends on the parameters, and the nature of the synthesis method that is arc discharge methodology [6], Laser ablation [7] and chemical vapour deposition (CVD) [7,8].Carbon Nanotubes were used for numerous composite applications showing the outstanding physical properties and mechanically they will exhibit elastic modulus in terms of TPa range [9]. CNTs have theoretical strength of 100 times than that of steel [10], although the exact magnitude of the value depends upon only on the diameter and chirality, Single-walled carbon Nanotubes and multi- walled carbon Nanotubes has high strength of 60 GPa and 6% for ultimate strain which have been reported [11, 12]. In CNTs/Alumina matrix the strength will be three times the toughness [13]. The single-walled carbon Nanotubes will shows the electric properties which will have a semi conducting or metallic character and also depends upon their chirality. Where as in the multi-walled carbon Nanotubes shows the metallic character and it is having the electrical conductivities in the range of 10^5 - 10^6 s/cm that have been reported for MWCNTs [14]. The plain concrete have low tensile strength and is quasi-brittle which is vulnerable to the uncontrolled propagation of cracks; to overcome this advantage, a new concept of introducing additional material at the millimetres to Nano meter scale has been realized in recent years. Fibers at the millimetres, micro scale are a commonly used materials [15].Advanced technology with in this field of Nano materials, such as Carbon Nanotubes (CNTs), Nano silica, Nano TiO₂, Nano Fe₂O₃, and Nano Al₂O₃ has recent focused on the reinforcement of the cement motor. Carbon Nanotubes (CNTs) are available in two forms one is Single-walled carbon Nanotubes (SWCNTs) and the one is Multi-walled carbon Nanotubes (MWCNTs), it depends on the number of concentric tubes [16-18].The researchers has been worked on determining the performance index with in the field of mechanics, electricity and thermology [19-24].Carbon Nanotubes will have the outstanding mechanical, thermal and electrical properties. The MWCNTs will have range from 1.4nm to 100nm, whereas their lengths range from 0.1 to 100 micro meters [25-28].

In the SWCNTs the dimensions will starts from 0.4nm to 3nm where as in their lengths the dimensions will starts from 1 to 50 micro meters [25, 28]. But in the aspect ratio it is approximately 1000 times in general exceeding 10^7 at its limit [25, 28, and 29].The carbon atoms will have a chemical bonding atoms composed entirely of sp² bonds, similar to those of graphite and strengthen than sp³ bonds, making the carbon Nanotubes will be high in both modulus and strength. In SWCNTs tensile strength will reach up to 500 GPA, where the MWCNTs can reach only 10 GPA-63 GPA [24, 30]. The young's modulus of SWCNTs and MWCNTs are approximately 1 TPA and 0.21TPA respectively [28, 31]. The yield strain will be more than 10% [32]. When compared to capped one the open ended CNTs will have the higher chemical reaction [33].In the CNTs the

elastic modulus and the tensile strength are very less because of having the larger c-c bond compared to graphite [34]. Carbon Nano tubes are made with length to diameter ratio of up to 1, 32,000,000:1. It's larger than the other material. Which are valuable for engineering, optics, electronics and Nano technology [35, 36, and 37]. Carbon Nano tubes with all the above said properties will be used as additives to the structural materials.

II. SYNTHESIS OF CARBON NANO TUBES

The MWCNTs were initial known within the arc discharge methodology by Lijma [38]. This methodology will be used in the manufacture process of the carbon Nano fibers and fullerenes. The SWCNTs took two years for synthesis Lijma and Ichihashi [39] and Bethune et al [40]. The followed method of metal catalysts with in the arc discharge methodology. In the optical devices ablation process will be used to synthesis bundles of aligned SWCNTs with tiny diameter distribution by researchers [41]. Yacaman et al was first to use chemical vapour decomposition (CVD) for catalytic growth of the Carbon Nanotubes. For the synthesis of the Carbon Nanotubes different procedure are followed such as chemical vapour deposition.(CVD)[45], Arc discharge methodology (AD)[43] and Laser ablation (LA)[46]. Chemical vapour deposition (CVD) is the most employed technique [44] because under the particular conditions it will allow the collection of group of Carbon Nanotubes with well aligned structures and with the desired orientation of the layers [47]. The different methods of carbon Nanotubes preparation can be consulted through recent reviews by Szabo et al [48] and Prasek et al [49].

III. CARBON NANOTUBES ADDITIONS

Carbon Nanotubes and carbon fibers (CNFs) have showed a very good improvement in terms of strength in the cement based composites. Carbon Nanotubes will have the extraordinary properties [63]. Carbon Nanotubes will have excellent young's modulus, elastic behaviour and high tensile strength [64] and extraordinary thermal property [65]. There is no proof of Carbon Nanotubes commercially available especially for construction materials [62], some of the trails shown that the significant improvement in hardness, compressive strength and young's modulus. Carbon Nanotubes addition will increase the the compressive strength by 50% [66] almost 600% increase in hardness at the early age of hydration [67] and greater than the 200% increase in young's modulus [68].

IV. CARBON NANO TUBES AND NANO FIBERS

Carbon Nanotubes/Nano fibers were used as the Nano reinforcement in cement based materials. CNTs/CNFs will give the greater strength in terms of modulus of elasticity (TPA) and the tensile strength (GPA) and it has distinctive chemical and electronic properties [69-71]. CNTs/CNFs Nano materials can strengthen the mechanical properties of the cement based materials [72, 73]. CNFs, SWCNTs and MWCNTs are highly structured graphene ring based on high aspect ratio (1000 or more)[74] and it is having a high surface areas. CNTs/CNFs were broadly studied in the polymeric composites [75-77]. In the present days carbon Nanotubes and carbon fibers were the most extensively used research materials. This area of research gives the surprising results, the researchers focus on CNTs (Carbon Nanotubes) addition in cement pastes than Carbon Nano fibers (CNFs) [72, 78-82]. Only a small number of investigations [73, 82] have dealt with the incorporating of the CNTs in to the mortar. The main challenge in the carbon Nanotubes /Nano fibers was proper dispersion that will be taken place in the cement paste, partially due to their hydrophobicity and some partially due to strong self attraction incorporating CNTs/CNFs in to the cement composites. The mechanical properties show the mixed results a good interaction bond between the CNTs/CNFs that has been observed.

V. METAL OXIDE NANO PARTICLE ADDITIONS

The main advantage of these Nano materials used in the construction industry was, its capability and good mechanical properties of the cement based structural materials, and the use of these Nano materials has the following advantages.

1. It gives the high strength in concrete for the particular applications.
2. It will cut back the quantity of cement in concrete so as to get similar strength and decreasing the price and therefore creating positive environmental impact on construction materials.
3. Nano materials will increase the strength in concrete within a short curing time and reduces the construction time period.
4. The addition of some of the metal Oxides present in the Nano particles in concrete, can reduce the permeability of concrete into ions. Because of this aspect the concrete will strengthen and there after we can improve the durability aspects.
5. TiO₂, Nano particles [50-52], Al₂O₃ Nano particles [53-55], ZrO₂ Nano particles [55], Fe₂O₃ Nano particle [53, 55-57], SiO₂ Nanoparticle [52, 53, 56-61] and Nano clay [21-24], inclusion in to the cement and concrete specimens shows improved mechanical properties.
6. The metal oxides Nano particles reacts with CaOH increasing the number of calcium silicate hydrate (C-S-H) gel, this produces the leading additional compacted microstructure and thereby decreases the permeability, and also improves the mechanical properties [58] such as flexure, compressive strengths and abrasion resistance [59].

VI. PROPERTIES OF THE CARBON NANO TUBES

A. Mechanical properties

Carbon Nanotubes has high stiffness and axial strength as a result of its carbon-carbon sp^2 bonding. The case of utilization of these carbon Nanotubes requires the fracture, elastic response, yield strength, inelastic behaviour and buckling. Carbon Nanotubes will have the stiffest fibre with young's modulus of 1.4 TPA and also the elongation failure of 20-30% which will have a tensile strength of 100 GPa .In case of the young's modulus the steel will have 200 GPa and the tensile strength will lies between 1GPa-2 GPa.

B. Thermal properties

Carbon Nanotubes shows that the thermal conduction will be double than that of the diamond. Carbon Nano tubes can have a special property of feeling cold to the bit, like metal, on the sides were the tube ends are exposed. Thermal conductivity and specific heat can be determined by using the phonons. The measurements of the thermo electric property of a Nanotube systems can offer the direct information carriers and therefore for the conduction mechanisms.

C. Strength

Carbon nanotubes are stiffest and strongest materials. In the year 2000 multi-walled carbon Nanotubes were tested [69] and it achieves a tensile strength of 63 gigapascals (GPa) and later in the year of 2008 it gains a strength of up to 100 GPa [70]. But in the case of individual, the carbon Nanotubes shows that strength will have extremely high and weak interactions between the adjacent shells because of its aspect ratio. Due to this sometimes carbon Nanotubes will reduces the strength and the carbon Nanotubes bundles will down to only a few GPA[71]. Multi-walled carbon Nanotubes the strength will reaches up to 60 GPA [70] and 17 GPA for double walled carbon Nanotubes.

D. Kinetic properties

Multi walled carbon Nanotubes will have the multiple concentric nanotubes with in one another, because of these it exhibit a striking telescope property where as in the inner nanotube will may slide without friction. Outer shell of the nanotube will creates an automatically perfect linear or rotational bearing.

E. Toxicity

The toxicity can play a key role in the field of the nanotechnology. The information are still to be fragmental and subject to criticism owing to the starting results which can highlight the issues with in the evaluating method of the toxicity of the heterogeneous material parameters like surface area, surface charge, surface chemistry, structure, sized distribution, agglomeration. The state of the samples can have bound impact on the carbon nanotubes. But the results show that the carbon nanotubes can cross the membrane barriers. If the raw materials reaches the organs, this will create the harmful effects like inflammatory, fibrotic reactions for the human beings [72], if these carbon nanotubes enter into human cells it accumulate in the cytoplasm which will even lead to death [73].

VII. APPLICATIONS OF THE CARBON NANOTUBES

Carbon Nanotubes will have a numerous applications in various application fields like Civil engineering, energy sector, medicine sector, environmental, electronic sector etc. Carbon Nanotubes will have remarkable applications in the concrete structures. Researchers identified that the carbon nanotubes can fill these voids in to the conventional type of concrete. Because of these voids, water can penetrate and it will cause concrete cracks. The filling voids in conventional concrete can reduce the cracks. Carbon Nanotubes and carbon Nano fibers will gives the greater strength with high modulus of elasticity it is represented in terms of TPA and the tensile strength will be represented in the order of GPA and this will have a special chemical properties and electronic properties [74-76]. Adding of weight percentage of MWCNTs to the epoxy resin will increase the fracture toughness and stiffness by 23% and 6% respectively. But at the same time carbon nanotubes will be good at enhancing the mechanical properties. These increases will depend upon the diameter, dispersion, alignment, aspect ratio and interfacial interaction with the matrix. According to theoretical aspect SWCNTs will have a young's modulus as high as 1TPA. other enhancements are strength characteristics carbon nanotubes will be good at the mechanical properties, as well as self compacting concrete and resistance to chloride penetration, and because of these properties shrinkage and permeability will be reduced [77, 78]. Primarily carbon nanotube will have the mechanical properties of the reinforcement in composite materials. Carbon Nanotubes will behaves in a different way in the response of a load. By using these carbon nanotubes a sensor has been inserted in to the concrete structures as crack indicators. Carbon Nanotubes is facing a major challenge in the availability and the cost aspects. There is no available techniques that can produce a large amount of carbon Nanotubes with pureness and excellence in terms of kilogram amounts. At present the carbon nanotubes price will be very high for commercial applications. In the initial stage carbon Nano fibers/fullerenes were also very high. But the present scenario has been totally changed in the carbon Nanotubes in the last 2-3 years. Several companies came forward to start and manufacture the carbon Nanotubes. If we overcome these challenges in the carbon

Nanotubes aspects, this will become a most innovative and useful material in the construction industry in the concrete structures.

VIII. CONCLUSION

1. Carbon Nanotubes will have the excellent properties in various applications fields like civil engineering, energy sector, medicine sector, environmental ,electronics sector etc. a plenty of research work has been done and the test results shows that the carbon Nano tubes having the excellent potential in various application fields.

2. By adding these carbon Nanotubes in cement and concrete specimens, the results observed shows that the mechanical properties has been increased significantly. Good interaction takes place between the cement paste and the carbon Nanotubes. Carbon Nanotubes are dispersed uniformly throughout the cement mortar without any aggregation of the carbon Nanotubes. Good interaction takes place between the fly ash cement and the carbon Nanotubes composites has been identified through research.

3. Compressive strength will increase with the fly ash mixes. The increase of the carbon nanotubes will give high strength. The specimens with high strain loadings and with optimal addition of the carbon nanotubes, the strength of the composite will be increased.

4. Inclusion of the carbon nanotubes shows the flexural strength will get increased with the high aspect ratios of the carbon nanotubes. In plain cement the strength will be very low. Flexural strength directly depends upon the concentration of the carbon nanotubes. When compared to carbon nanofibers, carbon Nanotubes will give the good flexural strength.

5. When the samples are reinforced with the carbon Nanotubes, young's modulus will be greater than the plain cement composites.

REFERENCES

- [1] Iijima S, "Helical microtubes of graphitic carbon", *Nature* 1991; 354(7):56–58.
- [2] Lau KT and Hui D, "The revolutionary creation of new advanced materials", carbon nanotube composites, *Composites: Part B* 2002; 33:263–277.
- [3] Grobert N, "Carbon nanotubes becoming clean", *Mater Today* 2007; 10(1–2):28–35.
- [4] Dai H, "Carbon nanotubes: opportunities and challenges", *Surf Sci* 2002; 500:218–241.
- [5] Popov VN, "Carbon nanotubes: properties and application", *Mater Sci Eng R* 2004;43(3):61–102.
- [6] Ando Y, "The preparation of carbon nanotubes", *Fuel Sci Technol* 1994;2(2):173–180.
- [7] Maser WK, Benito AM and Martinez MT, "Production of carbon nanotubes the light approach", *Carbon* 2002;40(10):1685–1695.
- [8] Oncel C and Yurum Y, "A review on the effect of reaction parameters", *Carbon Nanostruct* 2006;14:1737.
- [9] Salvétat JP, Bonard JM, Thomson NH, Kulik AJ, Forro L, Benoit W, "Mechanical properties of carbon nanotubes", *Appl Phys A* 1999;69(3):255–260.
- [10] Wong EW and Sheelan PE, "Nanobeam mechanics: elasticity, strength, and toughness, of nanorods and nanotubes", *Science* 1997;161–167.
- [11] Yu MF, Lourie O, Dyer MJ, Moloni K, Kelly TF, RuoffRS, "Strength and breaking mechanism of multiwalled carbon nanotubes under tensile load", *Science* 2000;287:637–640.
- [12] Walters DA, Ericson LM, Casavant MJ, Liu J, Colbert DT, Smith KA, "Elastic strain of freely suspended single-wall carbon nanotube ropes", *ApplPhysLett* 1999;74(25):3803–3805.
- [13] Zhan GD, Kuntz JD, Wan J, Mukherjee AK, "Single-wall carbon nanotubes as attractive toughening agents in alumina-based nanocomposites", *Nature Mater* 2003;2(1):38–42.
- [14] Ebbesen TW, Lezec HJ, Hiura H, Bennett JW, Ghaemi HF, ThioT, "Electrical conductivity of individual carbon nanotubes", *Nature* 1996;382(4):54–56.
- [15] Sun S, Yu X, Han B and Ou J, " In situ growth of carbon nanotubes/carbon nanofibers on cement/mineral admixture particles: a review", *ConstrBuildMater* 2013;49:835–840.
- [16] Iijima S, "Helical microtubules of graphitic carbon", *Nature* 1991;354(6348):56–58.
- [17] Bethune D, Klang C, De Vries M, Gorman G, Savoy R and Vazquez J, "Cobalt catalysed growth of carbon nanotubes with single atomic-layer walls", *Nature* 1993;363:605–607.
- [18] Iijima S and Ichihashi T, "Single-shell carbon nanotubes of 1-nm diameter". *Nature* 1993; 363:603–605.
- [19] Treacy MJ, Ebbesen T and Gibson J, "Exceptionally high Young's modulus observed for individual carbon nanotubes", *Nature* 1996; 381:678–680.
- [20] Yakobson BI, Brabec C and Bernholc J, "Nano mechanics of carbon tubes: instabilities beyond linear response", *Phys Rev Lett* 1996;76(14):2511.
- [21] Cornwell C and Wille L, "Elastic properties of single-walled carbon nanotubes in compression", *Solid State Commun* 1997;101(8):555–558.
- [22] Berber S, Kwon Y-K and Tománek D, "Unusually high thermal conductivity of carbon nanotubes", *Phys Rev Lett* 2000;84(20):4613.
- [23] Prylutskyy YI, Durov S, Ogloblya O, Buzaneva E and Scharff P, "Molecular dynamics simulation of mechanical, vibrational and electronic properties of carbon nanotubes", *Comput Mater Sci* 2000;17(2):352–355.
- [24] Yu M-F, Lourie O, Dyer MJ, Moloni K, Kelly TF and Ruoff RS, "Strength and breaking mechanism of multi-walled carbon nanotubes under tensile load", *Science* 2000;287(5453):63740.
- [25] Chan LY and Andrawes B, " Finite element analysis of carbon nanotube/cementcomposite with degraded bond strength", *Comput Mater Sci* 2010;47 (4):994–1004.
- [26] Konsta-Gdoutos MS, Metaxa ZS and Shah SP, "Multi-scale mechanical and fracturecharacteristics and early-age strain capacity of high performance carbon nanotube/cement nanocomposites", *CemConcr Compos* 2010;32(2):110–115.
- [27] Materazzi AL, Ubertini F and D'Alessandro A, "Carbon nanotube cement-based transducers for dynamic sensing of strain", *CemConcr Compos* 2013;37:2–11.
- [28] Han B, Sun S, Ding S, Zhang L, Yu X and Ou J, " Review of nano carbon-engineered multifunctional cementitious composites", *Appl Sci Manuf* 2015;70:69–81.

- [29] Wang G-W, Zhao Y-P and Yang G-T, "The stability of a vertical single-walled carbon nanotube under its own weight", *Mater Des* 2004;25(6):453–457.
- [30] Xie X, Mai Y, Zhou X. Dispersion and alignment of carbon nanotubes in polymer matrix: a review. *Mater Sci Eng: R: Rep* 2005;49(4):89–112.
- [31] Konsta Gdoutos MS, Aza CA, "Self sensing carbon nanotube (CNT) and nanofiber (CNF) cementitious composites for real time damage assessment in smart structures", *CemConcr Compos* 2014:162–169.
- [32] Makar J, Margeson J and Luh J, "Carbon nanotube/cement composites-early results and potential applications", *Innovations and Structural Implications*; 2005, p. 1–10.
- [33] Zhou G, Duan W, "Qualitative and quantitative descriptions on the localized electronic structure in single, walled carbon nanotubes. *J ChemPhys* 2002, 116(5):2284–2288.
- [34] Zhou G, Duan W, "First-principles study on morphology and mechanical properties of single-walled carbon nanotube", *ChemPhysLett* 2001,333(5):344–349.
- [35] N. Crainic, A.T. Marques, "Nano-composites: a state of the art review", *Key Eng. Mater.* 230–232 (2002) 656.
- [36] K.S.a.M.F. Gutierrez, "How Nanotechnology can change the Concrete World", 2005.
- [37] T. Ferdiansyah, H.A. Razak, "The properties of nanocarbon tubes cement mortar incorporating mineral additives", *International Conference on Advanced Material and Manufacturing Science, ICAMMS 2012* 2014, TransTech Publications, Beijing, 383–387, 2012.
- [38] S. Iijima, "Helical microtubules of graphitic carbon", *Nature (London)*, 1991.
- [39] S. Iijima, T. Ichihashi, "Single-shell carbon nanotubes of 1-nm diameter", London, 1993.
- [40] D.S. Bethune, C.H. Kiang and M.S. de Vries, "Cobalt-catalysed growth of carbon nanotubes with single-atomic-layer walls", London, 1993.
- [41] A. Thess, R. Lee, P. Nikolaev, H. Dai, "Crystalline ropes of metallic carbon nanotubes", 1996.
- [42] M.J. Yacaman, M.M. Yoshida and L. Rendon, J.G. Santiesteban, "Catalytic growth of carbon microtubules with fullerene structure", *Appl. Phys. Lett.* 1993.
- [43] S. Iijima, "Helicoidal microtubules of graphitic carbon", *Nature* 354 (1991) 56–58.
- [44] V. Patel, "Global carbon nanotubes market, *Nanotech Insights*", 2 (2011) 21–35.
- [45] A. Huczko, "Synthesis of aligned carbon nanotubes", *Appl. Phys. A* 74 (2002)617–638.
- [46] A. Thess, R. Lee, P. Nikolaev, "Crystalline ropes of metallic carbon nanotubes", *Science* 273 (1996) 483–487.
- [47] H.M. Cheng, F. H.Y. Pan, and L.L. He, "Large-scale and low-cost synthesis of single-walled carbon nanotubes by the catalytic pyrolysis of hydrocarbons", *Appl. Phys. Lett.* 72 (1998) 3282–3284.
- [48] A. Szabó, C. Perri, A. Csató, and G. Giordano, "Synthesis methods of carbon nanotubes and related materials", *Materials* 3 (2010) 3092–3140.
- [49] J. Prasek, J. Drbohlavova, and J. Chomouck, "Methods for carbon nanotubes synthesis-review", *J. Mater. Chem.* 21 (2011) 15872–15884.
- [50] Nazari A, Riahi S, "The effects of TiO₂ nanoparticles in flexural damage of self-compacting concrete". *Int J Damage Mech* 2011;20:2049–2072.
- [51] Nazari A, Riahi S, "TiO₂ nanoparticle effects on physical, thermal and mechanical properties of self compacting concrete with ground granulated blast furnace slag as binder". *Energy Build* 2011;43:995–1002.
- [52] Zhang M-H, Li H, "Pore structure and chloride permeability of concrete containing nano-particles for pavement". *ConstrBuild Mater* 2011;25:608–16.
- [53] Oltulu M, Sahun R, "Single and combined effects of nano-SiO₂, nano Al₂O₃ and nano-Fe₂O₃ powders on compressive strength and capillary permeability of cement mortar containing silica fume". *Mater Sci Eng A* 2011;528:7012–9.
- [54] Nazari A, Riahi S, "Improvement compressive strength of concrete in different curing media by Al₂O₃ nanoparticles". *MaterSciEng A* 2011;528:1183–91.
- [55] Shekari AH, Razzaghi MS, Influence of nano particles on durability and mechanical properties of high performance concrete. *ProcEng* 2011;14:3036–3041.
- [56] Li H, Xiao H-G and Yuan J, "Microstructure of cement mortar with nano-particles", *Compos Part B – Eng* 2004;35:185–189.
- [57] Li H, Xiao H-G, "A study on mechanical and pressure-sensitive properties of cement mortar with nanophase materials", *CemConcr Res* 2004;34:435–438.
- [58] Senff L, Hotza D and Lucas S, "Effect of nano-SiO₂ and nano-TiO₂ addition on the rheological behavior and the hardened properties of cement mortars", *Mater Sci Eng* 2012;532:354–361.
- [59] Chen L, Lin DF, "Applications of sewage sludge ash and nano-SiO₂ to manufacture tile and construction material", *Constr Build Mater* 2009;23:3312–20.
- [60] Jo B-W, Kim C-H, "Characteristics of cement mortar with nano-SiO₂ particles", *ACI Mater J* 2007; 104:404–407.
- [61] Nazari A and Riahi S, "The effects of SiO₂ nanoparticles on physical and mechanical properties of high strength compacting concrete", *Compos Part B – Eng* 2011;42:570–578.
- [62] van Broekhuizen P, van Broekhuizen F, Cornlissen R and Reijnders L, "Use of nanomaterials in the European construction industry and some occupational health aspects thereof", *Nanopart Res* 2011;13:447–462.
- [63] Raki L, Beaudoin J, Alizadeh R, Makar J and Sato T, "Cement and concrete nanoscience and nanotechnology", *Materials* 2010;3:918–942.
- [64] Walters DA, Ericson LM, Casavant MJ, Liu J, Colbert DT and Smith KA, "Elastic strain of freely suspended single-wall carbon nanotube ropes", *ApplPhysLett* 1999;74:38035.
- [65] See CH and Harris AT, "A review of carbon nanotube synthesis via fluidized-bed chemical vapor deposition", *IndEngChem Res* 2007;46:997–1012.
- [66] Cwirzen A, Habermehl-Cwirzen K and Penttala V, "Surface decoration of carbon nanotubes and mechanical properties of cement/carbon nanotube composites", *Adv Cem Res* 2008;20:65–73.
- [67] Makar J and Chan GW, "Growth of cement hydration products on single-walled carbon nanotubes", *J Am Ceram Soc* 2009;92:1303–1310.
- [68] de Ibarra YS, Gaitero JJ, Erkizia E and Campillo I, "Atomic force microscopy and nano indentation of cement pastes with nanotube dispersions", *Phys Status Solidi A* 2006;203:1076–1081.
- [69] Yu MF, Lourie O, Dyer MJ, Moloni K, Kelly TF, Runoff RS, "Strength and breaking mechanism of multi-walled carbon nanotubes under tensile load", *Science* 2000;287(5453):637–640.
- [70] Peng B, Locascio M, Zapol P, Li S, Mielke SL and Schatz GC, "Measurements of near-ultimate strength for multi walled carbon nanotubes and irradiation induced cross linking improvements", *Nat Nanotechnol* 2008;3(10):626–631.
- [71] Filletier T, Bernal R, Li S and Espinosa HD, "Ultra-high strength and stiffness in crosslinked hierarchical carbon nanotube bundles", *Adv Mater* 2011;23(25):2855.

- [72] Kolosnjaj J, Szwarc H and Moussa F, “ Toxicity studies of carbon nanotubes”.,*Adv ExpMed Biol* 2007;620:181–204.
- [73] Porter A, Gass M, Muller K, Skepper JN, Midgley PA and Welland M, “ Direct imaging of single-walled carbon nanotubes in cells”
Nat Nanotechnol 2007;2(11):713–717.
- [74] Ajayan PM, “ Nanotubes from carbon”, *Chem Rev* 1999;99:1787–1799.
- [75] Salvetat J-P, Bonard J-M, Thomson NH, Kulik AJ, Forro L and Benoit W, “Mechanical properties of carbon nanotubes”, *ApplPhys Mater Sci Process* 1999;69:255–260.
- [76] Srivastava D, Wei C and Cho K, “ Nanomechanics of carbon nanotubes and composites”, *ApplMech Rev* 2003;56:215–230.
- [77] Chang T-P, Shih J-Y, Yang K-M and Hsiao T-C, “ Material properties of Portland cement paste with nano-montmorillonite”, *J Mater Sci* 2007;42(17):7478–7487.
- [78] Kuo W-Y, Huang J-S and Lin C-H, “ Effects of organo-modified montmorillonite on strengths and permeability of cement mortars.”
CemConcr Res 2006;36(5):886–895.

AUTHOR PROFILE

Author1 Mr. A. Vijaya bhaskar: He had Completed B. Tech degree in the Department of civil Engineering from SPEC Nellore, and M. Tech in Structural Engineering from VIT Chennai, Pursuing his PhD degree under the guidance of Dr M.Shanmugasundaram. He has one international research publications to his credits. He has one year experience in Teaching. His doing research in Multi-walled Carbon nanotubes.

Author2 Dr M.Shanmugasundaram: He had completed his B.E degree in Civil Engineering from RCET Madurai, M.E in Structural Engineering, TCE Madurai. He completed his Ph.D on 2014 under the esteemed guidance of Dr. K.Sudalaimani, Associate Professor, TCE, Madurai. He has 7 international research publications to his credits. He had filed two patents during the year 2015. He has 3 years of industrial experience and 8 years of teaching experience. His recent research interests include, sustainable materials and polymer concretes.